



## COMFORT SA SLAB 50

### High performance Slabs for building insulation



#### Excellent Thermal Insulation

Thermal conductivity ( $\lambda$ ) of 0.036 (W/m.K) at 24 °C provides excellent thermal performance, reducing heat loss for residential and commercial buildings.



#### Excellent Acoustic Insulation

Comfort SA Slabs provides optimal acoustic performance for better comfort.



#### Effective Fire Protection

Comfort SA Slabs are non-combustible and classified as A1 Euro-class Reaction to fire.



# COMFORT SA SLAB 50

Characteristic	Symbol	Unit	Quantities and measured values	Standard
Description	KIMMCO ISOVER stone wool products are made from volcanic rock – a natural material present in large quantities throughout the earth. These raw materials are natural basalt and dolomite coming from Saudi Arabia, our product is compliance with <b>ASTM C612</b> and <b>EN 13162</b> standard.			
Thermal Conductivity	$\lambda$	( W /m·K )	0.036 at 24°C	EN 12 667 ASTM C518 ASTM C177
Density	$\rho$	(kg/m <sup>3</sup> )	50	EN 1602
Thickness	T	(mm)	170.0	EN 823 ASTM C303
Maximum Service Temperature	°C	-	+750 +100	ASTM C411
Max (Fiber)				
Max (Facing)				
Reaction to Fire Class	-	-	Non-combustible Euro-class <b>A1</b>	EN 13501-1 ASTM E136
Flame Spread	-	-	15	ASTM E84
Smoke Development	-	-	5	ASTM E84
Specific Thermal Capacity	c	(KJ/Kg.K)	~1	EN 10 456 ASTM C518
Shot Contents	-	(%)	≤ 10% from the weight	ASTM C612
Water Vapour Sorption	-	(%)	< 1% by weight	ASTM C1104
Water Vapour Diffusion Resistance Factor	$\mu$	-	~1	EN 12 086
Facing	One side FSK Faced			
Miscellaneous Delivery Forms	Our products are supplied in polyethylene packing. As mentioned in the MSDS product should be stored in a dry conditions.			

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. For further information, please contact our team. We deliver only according to our terms of trade and terms of delivery.

[www.siiimco.com.sa](http://www.siiimco.com.sa)

**KIMMCO ISOVER**  
SAINT-GOBAIN